

Selection & Specification Data

| | |
|----------------------------|--|
| Generic Type | Waterborne epoxy insulative coating |
| Description | Carbotherm 551 is a unique insulative composite coating formulated in a high temperature resistant epoxy binder. Unlike acrylic-based insulative materials it has superior toughness, hardness, impact resistance, chemical resistance and permeation resistance. It is therefore more suitable for industrial applications or other physically demanding environments. It is an ideal protective heat barrier to shield personnel from hot surfaces. It also inhibits heat transfer into or out of a structure. Its insulative properties keeps structures exposed to solar radiation significantly cooler. It can be used to minimize or eliminate condensation of pipes or other operating equipment. Its superior application properties of higher film build per coat and fewer coats offers savings and quicker return to service. |
| Features | <ul style="list-style-type: none"> • Excellent thin-film insulation • Unique epoxy formula outperforms acrylic-based materials • Tougher and more durable than acrylic coatings • Higher chemical resistance than acrylic coatings • Topcoats are optional • Protects personnel from hot surfaces • Ideal for industrial/aggressive applications • Insulation provides anti-condensation properties • Acceptable for use in USDA facilities • High film build per coat; fewer coats • Low VOC; low odor • May be applied to hot surfaces |
| Color | Off White (0800) only. See Topcoat. |
| Finish | Eggshell |
| Primer | Priming is not required for insulation performance. For long term corrosion performance at the following service temperatures: Up to 300°F/149°C: Use Carbozinc 11 Series; Carboguard 690, or Carbomastic 15 Series Up to 350°F/176°C: Use Carbozinc 859 Series, Thermaline 450 EP, Thermaline 400 GS or Thermaline 450 Novolac. |
| Topcoat | Topcoats are optional to provide gloss, custom colors, prevent dirt pick-up, or prevent mildew. Acceptable topcoats include Sanitile 555, Carbothane 134 WB, or Carbocrylic 3359 Series. Topcoat is recommended for use in USDA facilities. |
| Service Temperature | -60° to 350°F (-51° to 176°C) For initial service avoid sudden temperature "surges". Do not exceed 200°F/93°C during the first hour. |
| Dry Film Thickness | 35.0 - 40.0 mils (889 - 1016 microns) per coat Number of coats depends on the operating temperature and degree of insulation or protection needed. Contact your local Carboline Representative for a copy of Carbotherm 551 Specifiers Guide for thickness needs based on end use. |
| Solids Content | By Volume 82% +/- 2% Tested in accordance with ASTM D2697 |

Selection & Specification Data

| | |
|----------------------------------|---|
| Theoretical Coverage Rate | 1315 ft ² at 1 mil (32 m ² /l at 25 microns) 38 ft ² at 35 mils (0.9 m ² /l at 875 microns) 33 ft ² at 40 mils (0.8 m ² /l at 1000 microns) |
| | Allow for loss in mixing and application. |
| VOC Values | As Supplied 37 grams/liter Calculated per EPA Method 24. |

Substrates & Surface Preparation

| | |
|------------------------|--|
| General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil, and all other contaminants that could interfere with adhesion of the coating. |
| Steel | Prime with appropriate primers as recommended or specified in section on "Primers". |
| Stainless Steel | Abrasive blast to a 1-1.5 mil profile and apply material direct to substrate or over appropriate non-zinc primer (See Primers). |

Performance Data

| Test Method | System | Results |
|---|--|---|
| Adhesion (ASTM D4541) | Carbotherm 551 | 1000 psi typical (6.9 MPa) |
| Cyclic QUV-A/Prohesion (ASTM D5894) | Carbotherm 551 over the following primers: Carbozinc 859, Carbozinc 11 HS, or Carbomastic 15 | 2016 hours No rusting or blistering in the plane or scribe |
| Direct Impact (ASTM D2794) | Carbotherm 551 | 160 lbs; Indentation only; no cracking; no disbondment |
| Emissivity (ASTM E408) | Carbotherm 551 | 0.85 |
| Flame Spread (ASTM E84) | Carbotherm 551 | Class A Rating Flame Spread Index: 0 Smoke Developed Index: 5 |
| Humidity Cabinet (ASTM D2247) | Carbotherm 551 over the following primers: Carbozinc 859, Carbozinc 11 HS, or Carbomastic 15 | 2016 hours No blistering or rusting in the plane or scribe |
| R-Value (per inch) (ASTM C518) | Carbotherm 551 | 2.223 hr ft ² °F/BTU |
| Shore D Hardness (ASTM D2240) | Carbotherm 551 | 55 |
| Solar Reflectivity (ASTM E903) | Carbotherm 551 | 84.7 |
| Tensile Strength (ASTM D638) | Carbotherm 551 | 800 psi (5.48 MPa) |
| Thermal Conductivity (ASTM C177) (at 23°C; 50°C; 149°C) | Carbotherm 551 (tested at 0.2309") | 23°C: 0.0952 W/m-°K 50°C: 0.0952 W/m-°K 149°C: 0.1099 W/m-°K |

Carbotherm[®] 551

Mixing & Thinning

Mixing This is a two component product and separation of the Part A may occur and is common. Turn Part A containers upside down for 5 minutes prior to mixing to dramatically improve blending. Use a drywall compound mixing paddle (in reverse) to incorporate material to a homogeneous consistency resembling a milkshake. Normally this will take several minutes. Avoid contact of mixing blade and edge of plastic buckets to avoid shearing plastic pieces into coating. If other types of blades or high powered mixers are used, avoid high shear or over mixing. Once redispersed add the Part B while mixing until uniform; usually 3-5 minutes.

Thinning No thinning is required.

Ratio By volume: 16:1 (Part A to Part B)

Pot Life 1 hour at 75°F/23°C.

Application Equipment Guidelines

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) Pre-rinse (and lubricate) equipment with undiluted Carboline Surface Cleaner 3 followed by clean potable water before spraying. The following spray equipment has been found suitable and is available from WIWA[®] or other equipment manufacturers.

*WIWA is a registered trademark of the Wilhelm Wagner GmbH & Co. KG

Conventional Spray Not recommended.

Airless Spray Pump Ratio: 30:1 (min.)*
GPM Output: 3.0 (min.)
Material Hose: 3/8" I.D. (min.)
Tip Size: .021-.025***
Output PSI: 1800-2200
Filter Size: Remove filters
*PTFE packings are recommended and available from the pump manufacturer. Use of a surge protector is strongly recommended.
**Use heavy duty reverse-a-clean non-diffuser tips.

Trowel Trowel application may be used. Do not apply more than 40 mils (1 mm) per coat and do not use excessive water when smoothing.

Brush & Roller (General) Multiple coats may be required to achieve recommended dry film thickness. Brushing may be used but may negatively affect insulative properties due to uneven thickness. Avoid excessive re-brushing. Roller application is difficult and not normally recommended.

Brush Use a synthetic bristle brush. Use for touch up of small surface areas only.

Roller Not recommended

Application Conditions

| Condition | Material | Surface | Ambient | Humidity |
|-----------|----------------|-----------------|----------------|----------|
| Minimum | 50 °F (10 °C) | 50 °F (10 °C) | 50 °F (10 °C) | 0% |
| Maximum | 100 °F (38 °C) | 250 °F (121 °C) | 110 °F (43 °C) | 80% |

It is best to spray apply a light 5-10 mil coat and allow to tack dry prior to full coating. This is especially helpful over hot surfaces (150-250°F/65-121°C) which may require 2-4 light passes. Do not apply when the surface temperature is less than 5°F (3°C) above the dew point. Do not apply if temperatures are expected to drop below 50°F (10°C) within 24 hours of application. Special application techniques may be required above or below normal application conditions. Dry times will be aided by higher temperatures, lower humidity, hotter substrates, and more air movement during application and curing.

Curing Schedule

| Surface Temp. & 50% Relative Humidity | Dry to Recoat |
|---------------------------------------|---------------|
| 60 °F (16 °C) | 10 Hours |
| 75 °F (24 °C) | 5 Hours |
| 90 °F (32 °C) | 3 Hours |

These times are based on a 40 mil (1000 micron) dry film thickness. Higher film thicknesses, insufficient ventilation, high humidity or cooler temperatures will require longer cure times. If a final color coat (see Topcoats) is used; allow 24 hours dry time (at 75°F/23°C) to ensure adequate dryness prior to final color coat.

Cleanup & Safety

Cleanup Use clean potable water followed with suitable solvent to dry equipment. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Keep container closed when not in use.

Packaging, Handling & Storage

Shelf Life Part A: 24 months at 75°F (24°C)
Part B: 24 months at 75°F (24°C)

Shipping Weight (Approximate) 4.25 Gallons
27 lbs (12 kg)

Storage Temperature & Humidity 40° -110°F (4°-43°C)
0-95% Relative Humidity

Flash Point (Setaflash) Part A: >200°F (93°C)
Part B: 99°F (37°C)

Storage Store indoors (Keep from freezing)



An **RPM** Company

October 2014

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline[®] and Carboguard[®] are registered trademarks of Carboline Company.